



# TECTUL

## Lamina alfajor acero al carbón


MATERIALES



CARACTERÍSTICAS DIMENSIONALES



APLICACIONES



Calidad	Composición química			
ASTM 569	C	Mn	P	S
	15	60	3,5	1,0

Propiedades Macánicas		
Límite elástico	Resistencia a la tracción	Alargamiento [%]
250 [MPa]	365 [MPa]	22

MATERIALES



Láminas según norma ASTM A569 fabricadas mediante laminación en caliente, grabadas en alto relieve en forma de lágrimas para hacerlas antideslizantes.

APLICACIONES



Usada en carrocerías, plataformas industriales, escaleras, pisos, industria automotriz.

CARACTERÍSTICAS DIMENSIONALES



Se manejan presentaciones desde 1x3 [m] hasta 1x21 [m] y el espesor varía desde 2.5 [mm] hasta 12,7 [mm]

\* Fotos y medidas referenciales, sujetas a cambios sin previo aviso por parte del proveedor o fabricante.



# TECTUL

# Alfajor carbon steel sheet

MATERIALS

CHARCATERISTICAS DIMENSIONALES

APPLICATION



Qualities	Chemical composition			
	C	Mn	P	S
ASTM 569	0	2	0,045	0,030

Mechanical proprieties		
Elastic limit	Tensile strength	Elongation [%]
250 [MPa]	365 [MPa]	22

**MATERIALS**  
 Sheets according to ASTM A569 standard, manufactured by hot rolling, engraved in high relief in the form of teardrops to make them anti-slip.

**APPLICATION**  
 Used in car bodies, industrial platforms, ladders, floors, automotive industry.

**DIMENSIONAL CHARACTERISTICS**  
 We handle presentations from 1x3 [m] to 1x21 [m] and the thickness varies from 2.5 [mm] to 12.7 [mm].

\* Reference photos and measurements, subject to change without prior notice from the supplier or manufacturer.